



MLPQ 5X5

RoHS Compliance Document

Contents:


1. Composition
2. Solder Reflow
3. Tin Whisker Report



MLPQ 5X5

Component	Material Name	Material Mass (g)	Element Name Composition	CAS #	Substance Mass (g)	Material Analysis Weight (%)	% of Total Weight
Chip	Silicon	0.00201	Si	7440-21-3	0.00201	100%	2.9%
Encapsulant	Epoxy Resin	0.03199	SiO2	7631-86-9	0.02082	65%	30.2%
			Epoxy Resin	90598-46-2	0.01117	35%	16.2%
Lead Frame	Copper	0.03312	Cu	7440-50-8	0.03220	97%	46.7%
			Fe	7439-89-6	0.00092	3%	1.3%
Die Attach	Silver Epoxy	0.00082	Ag	7440-22-4	0.00070	85%	1.0%
			Epoxy Resin	90958-46-2	0.00012	15%	0.2%
Wire bond	Gold	0.00072	Au	7440-57-5	0.00072	100%	1.0%
Lead Finish	Matte Tin	0.00036	Sn	7440-31-5	0.00036	100%	0.5%
		0.06902	Total Weight (g)		0.06902		

* Tin whisker mitigation strategy is 150 C, 1 hour anneal within 24 hours of tin plating.



This part is compliant with EU Directive 2002/95/EC (RoHS) and does not contain lead, mercury, cadmium (0.01%), hexavalent chromium, PBB or PBDE in concentrations greater than 0.1%, except as permitted by Annex (7).



MLPQ 5X5

Test Definition	Test Conditions	Inspection Interval Class 1 and 2 Products	Total Duration Class 1 and 2 Products	Maximum Whisker Length (um)
Room Temperature Humidity Storage	30± 2°C/60± 3%RH	1000 hours	4000 hours	20
Temperature Humidity Unbiased	55± 3°C/85±3% RH	1000 hours	4000 hours	20
Temperature Cycling	-40 to 55°C to 80 to 95°C, air to air, 10 min soak, approx 3 cycles /hours	500 cycles	1500 cycles	45

Tin Whisker testing per JESD201, Environmental Acceptance Requirements for Tin Whisker Susceptibility of Tin and Tin Alloy Surface Finish

Tin Whisker Results (number of failing whiskers)

Test	1000 Hours	2000 Hours	3000 Hours	4000 Hours
Room Temperature Humidity Storage	0/24	0/24	0/24	0/24
Temperature Humidity Unbiased	0/24	0/24	0/24	0/24
Test	500 Cycles	1000 Cycles	1500 Cycles	
Temperature Cycling	0/24	0/24	0/24	